



POLYTONE SYNTHETIC RESINS

Alkyl Phenolic Resins

TECHNICAL DATA	POLYTONE AP 120
Chemical Classification	PTBP Formaldehyde Resin(Novolac)
Type	Non Heat Reactive/Tackifying Resin
Physical Form	Broken Lumps
Colour	Pale Yellow/light Reddish Brown
Softening Point (B & R)	92° C – 103 ° C
Acid Value	67 mg KOH/ g resin (Max)
Methylol Content	1.0% Max
Ash Content	0.1% Max
Acetone Insolubles	0.3% Max
Moisture Content	0.2% Max

<u>Properties & Usage</u>	POLYTONE AP 120 is a non heat reactive thermoplastic alkyl phenolic resin designed to develop high tack levels in rubber compounds which are used in tyre construction and mechanical goods. POLYTONE AP 120 is used as tackfier in the manufacture of rubber goods such as tire industry
<u>Applications</u>	Tyre /Tire Building, Conveyor Belts, Rubber Hose, Rubber Lining, Rubber Mats, Rubber Sheets, Reinforced Rubber, Fabric Lined Rubber, Rubber Adhesives, Rubber Goods and many more.
<u>Solubility</u>	POLYTONE AP 120 is soluble in esters, ketones, aromatic and aliphatic chlorinated hydrocarbons. Insoluble in alcohols.
<u>Compatibility</u>	Excellent compatibility in synthetic and natural rubbers. Blends easily into rubber stocks
<u>Packaging</u>	Available in 25 Kg bags
<u>Shelf Life</u>	Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred.

