



**polyols &
polymers**

POLYTONE SYNTHETIC RESINS **Modified Maleic Resins**

TECHNICAL DATA	POLYTONE M 131
Chemical Classification	Rosin Modified Maleic Resin
Type	Oil Soluble
Physical Form	Broken Lumps
Colour	Yellow to light brown
Softening Point (B & R)	125° C – 135 ° C
Viscosity of 50% solution in Toluene at 25° C by B 4 Ford Cup	30 - 40 sec
Acid Value	20 mg KOH/ g resin (Max)

<u>Application</u>	POLYTONE M 131 is used in Varnishes, Paints and Over Print Varnishes, N.C. Lacquers etc.
<u>Solubility</u>	POLYTONE M 131 is soluble Mineral Turpentine Oil and Toluene
<u>Packaging</u>	Available in 25 Kg bags
<u>Shelf Life</u>	Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred.

