



POLYTONE SYNTHETIC RESINS

Non Reactive Polyamide Resins

TECHNICAL DATA

POLYTONE PA 351

Chemical Classification	Polymeric Fatty Acid Based Polyamide Resin
Type	Spirit Soluble Grade
Physical Form	Broken Lumps
Colour	Bright light yellow
Softening Point (B & R)	140° C – 150 ° C
Viscosity of 35% solution in 1:1 ratio of Toluene:Butanol at 25° C by B 4 Ford Cup	24 -45 mPas
Acid Value	7 mg KOH/ g resin (Max)
Amine Value	7 mg KOH/ g resin (Max)

Application

POLYTONE PA 351 is an alcohol soluble non reactive polyamide resin in solid form suitable for flexographic printing inks. This resin exhibits good anti-blocking characteristics and finds use in specialized flexographic inks and release lacquers. Inks prepared from this resin have good adhesion to a variety of substrates, excellent solvent release properties, low odour and good nitrocellulose compatibility.

Solubility

POLYTONE PA 351 shows excellent solubility in a variety of solvents that do not attack rubber stereotypes. Under certain conditions the solutions forms reversible gels on standing and to avoid this, it is recommended to add small percentage of water or higher alcohols or aromatic hydrocarbon solvent. POLYTONE PA 351 has infinite solubility in ethanol and higher alcohols. It is soluble in methanol at higher concentrations – 40% and above.

Compatibility

POLYTONE PA 351 is compatible with ketonic, maleic, nitro cellulose, reduced phenolic and pure phenolic resins. However, compatibility with alkyds is only partial.

Packaging

Available in 25 Kg bags

Shelf Life

Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture.

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred.

